

VigoTwinOkoumé





Description	Poplar plywood core and okoumé outer faces, manufactured in compliance with current regulations							
Use	Nautical, furniture, DIY							
Classification by face appearance	Superior							
Release of formaldehyde	E1, CARB 2 , NAUF							
Gluing class	Class 1, Class 2							
	EN 314-2							
Sizes	250 × 122, 310 × 153 cm							
Thicknesses	from 3 to 40 mm							
	EN 315							
Dimensional tolerances	Length and width: +/-3,5 mm. Thickness +(0,2+0,03t); -(0,4+0,03t). Orthogonality: 1 mm/m							
	EN 315							
Properties	Standard	Unit	Thicknesses - Plies					
			8/5	10/5	12/7	15/7	18/9	25/11
Longitudinal flexural strength	UNI EN310	N/mm ²	30	28	27	24	25	29
Transverse flexural strength	UNI EN310	N/mm ²	28	24	27	28	22	29
Module of longitudinal flexural elasticity	UNI EN310	N/mm ²	3600	3500	3200	3000	2900	3300
Module of transverse flexural elasticity	UNI EN310	N/mm ²	3200	3100	3300	3800	3700	3200
								EN 310
Density	420 kg/m ³ +/- 10%							
	EN 323							
Thermal conductivity	0,12 W/m K							
	EN 12664							
Residual moisture	8 / 12%							
	EN 322							
Reaction to fire	D-s2,d0 - Dfl-s1 (for thicknesses > 9 mm)							
	EN 13501-1							

The data in this sheet show approximate values obtained from internal testing on normal production. It is the buyer's responsibility to determine whether the products of E.Vigolungo SpA are suitable for the applications for which they are intended to be used and that the modes of transport and use comply with current regulations.